

TechnoGrout™E2

Two-Component Epoxy Grout

PRODUCT DESCRIPTION

TechnoGrout™E2 is two-component solvent-free epoxy grout, with high mechanical resistance. With excellent workability, TechnoGrout™E2 epoxy resin grout is for use in situations where the gap between a base plate and substrate needs to be filled and the structural load be uniformly distributed. Just open the pail, remove the tray, add the hardener (component B) to the grout resin (component A) and it's ready to use. It's that easy.



Buildings
Structures



Transportation
Infrastructure



Water &
Wastewater



Oil, Gas &
Industrial



Waterfront
Structures



Industrial
Facilities

TECHNICAL DATA (DRY FIBER)

	Unit	TechnoGrout™E2
Density	Kg/m ³	1100
Working Time	(32 °C)	10-20 min
Shrinkage(7 day)		-0.0063
Tensile Strength(7 day)	MPa	14
Flexural Strength(7 day)	MPa	30
Mixing Ratio by Volume	Parts A:B	2:1

ADVANTAGES

- It is unaffected by acids, bases, corrosive cleaners, salt water, chlorine, etc.
- It has very good adhesion and is very durable.
- It can be applied very easily, on vertical and horizontal surfaces, and can be cleaned by using hard sponges and clean water.
- High compressive, tensile and flexural strengths
- Wide range of gap thicknesses are possible
- Low creep characteristics under sustained loading

TYPICAL USES

- Grouting of machinery and equipment with high load requirements.
- Structural grouting of baseplates, columns, beams, crane rails, bridge seats, dowels, etc.
- for surfaces that require high resistance to mechanical loads and chemical effects, as well as waterproofing.

PACKAGING

Component: A = 10 kg, B = 5 kg

Component: A = 20 kg, B = 10 kg

MIXING

- Pour the hardener (Part B) into a pail of grout resin (Part A) and stir by hand, using a spatula or paint stirring paddle, until well mixed to a uniform color.
- Alternatively, a slow speed drill and mixing paddle may be used, provided that the mixing does not produce a vortex in the material. Excessive mixing will pull air into the product, which may compromise the finished installation.

INSTALLATION PROCEDURE

PREPARATION OF SUBSTRATE

concrete surfaces should be clean, sound and as oil-and water-free as possible. Excessively damaged concrete should be removed.

APPLICATION

- The mixed grout should be poured steadily from one side only to eliminate the entrapment of air.
- Continuous grout flow is essential.
- Sufficient grout must be available prior to starting.
- The time taken to pour a batch should be regulated to the time taken to prepare the next batch.

STORAGE

Two years in original unopened



packaging when stored in dry conditions; high relative humidity will reduce shelf life.

CLEAN UP

Cured material must be removed mechanically.

FAIRST AID

Skin

Wash fibers off skin with water and soap. If fibers are embedded in the skin, remove with tweezers. Discard clothing that may contain embedded fibers. Seek medical advice if exposure results in adverse effects.

Eyes

Immediately flush with a continuous water stream for at least 20 minutes. Washing immediately after exposure is expected to be effective in preventing damage to the eyes. Seek medical advice.

Inhalation

If there is inhalation exposure to the fibers of this product, remove source of exposure and move victim to fresh air. If victim is not breathing, give artificial respiration. If there is breathing difficulty, give oxygen. Seek medical advice for any respiratory problems.

Ingestion

Ingestion is not a likely means of exposure for this product. If ingestion does occur, do not induce vomiting. Give nothing by mouth if victim is unconscious. Seek medical advice.

DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Technopol products makes no claim that these tests or any other tests, accurately represent all environments.
