TechnoGrout™NC

Nano Cement Grout



PRODUCT DESCRIPTION

The main components of TechnoGrout™NC, blast furnace slag and Portland cement clinker, are separately grinded and classified to the requested grade. These fractions are blended with selected gypsum to a regulated setting according to fixed formulas in a batch mixer into TechnoGrout™NC. The specification of the specific surface area (Blaine) isn't significant for ultrafine binders as it gives no information about the maximum grain size, which is the key parameter for grout ability.



Buildings Structures



Transportation Infrastructure



Water & Wastewater



Oil, Gas & Industrial



Waterfront Structures



Industrial Facilities

TECHNICAL DATA (DRY FIBER)		
	Unit	TechnoGrout™NC
Density	kg/l	1.7
Compressive Strength (28 days)	MPa	35
Modulus of Elasticity in Compression	GPa	9.6
Chemical Base		Modified nano cement
Viscosity	mPa∙s	~ 100
Mixing Ratio by Weight	Parts A:B	1:0.65

ADVANTAGES

- Structural grouts for cracks
- Corrosion protection of embedded reinforcements.
- Deep penetration into narrow cracks in concrete and mortar
- Good flow properties
- Filling of voids
- Final, rigid, cementitious sealing of cracks while simultaneously treating corroding or corrosion-prone reinforcing steel in concrete and mortar.

TYPICAL USES

- Waterproofing and stabilization of rock in tunneling
- Repair of concrete or mortar
- As a component for high performance concrete as a substitute for micro silica.
- Remedial cementing of oil and gas wells.
- To improve the early strength of light weight oil well cement slurries

MIXING

- TechnoGrout™NC is delivered in two precisely matched components. If required, a maximum of 0.2L water can be added.
- Place the liquid part B in a suitable mixing vessel. Mix with colloidal mixer at approx. 2800 rpm and add the powder part A slowly and continuously. Mix the suspension thoroughly for at least 3 minutes.
- Subsequently, pour the injection material directly into the pump or keep ready in a clean container.

INSTALLATION PROCEDURE

PREPARATION OF SUBSTRATE

The substrate must be sound, clean, free of oil and grease, old coatings and other contaminations. For good adhesion, pretreat the substrate with high pressure water or mechanically. Use air pressure to remove dust from cracks.

APPLICATION

The injection material can be injected with commercially available equipment designed for cement injections. For vertical injection sections, inject from bottom to top. If dry concrete has to be injected, it is recommended to pre-wet the concrete with water under light





pressure.

CLEAN UP

Clean tools with water immediately after use. Hardened material can only be removed mechanically.

FAIRST AID

Skin

Wash fibers off skin with water and soap. If fibers are embedded in the skin, remove with tweezers. Discard clothing that may contain embedded fibers. Seek medical advice if exposure results in adverse effects.

Eyes

Immediately flush with a continuous water stream for at least 20 minutes. Washing immediately after exposure is expected to be effective in preventing damage to the eyes. Seek medical advice.

Inhalation

If there is inhalation exposure to the fibers of this product, remove source of exposure and move victim to fresh air. If victim is not breathing, give artificial respiration. If there is breathing difficulty, give oxygen. Seek medical advice for any respiratory problems.

Ingestion

Ingestion is not a likely means of exposure for this product. If ingestion does occur, do not induce vomiting. Give nothing by mouth if victim is unconscious. Seek medical advice.

DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Technopol products makes no claim that these tests or any other tests, accurately represent all environments.

©Technopol products. All rights reserved.